



ARDEX X 18

Fibre Reinforced Flexible Non Slump Wall and Floor Tile Adhesive

Fibre reinforced for extra strength and peace of mind

Excellent workability with low sand content

Ideal for all tile types including fully vitrified, porcelain and mosaics

Non slump: ideal for large format and heavy tiles on floors & walls Flexible and with extended open time

Use over early age concrete/screeds and render

For internal and external use

Suitable for swimming pools and wet areas

Low VOC content



ARDEX Singapore Pte Ltd
26 Tuas Ave 4
Singapore 639376
Tel: +65 6861 7700
Fax: + 65 6862 3381
Email: sales@ardex.com.sg
Website: www.ardex.com.sg

ARDEX X 18

Fibre Reinforced Flexible Non Slump Wall and Floor Tile Adhesive

DESCRIPTION

ARDEX X 18 is a superior white polymer fortified cement-based wall and floor tile adhesive that has been specially formulated with mastic type properties. It contains specially developed fibres that add strength to the tiled area. ARDEX X 18 has an extended open time, is non slump and flexible. For internal and external use in residential and commercial applications, including swimming pools. Low VOC content.

FOR FIXING TILE TYPES

Fully vitrified and ceramic tiles, porcelain, natural stones (excluding moisture sensitive) and mosaics.

TO (SUBSTRATES)

- Concrete, renders, screeds
- Fibre-cement sheet, plasterboard on walls
- Compressed fibre-cement sheet on floors
- ARDEX liquid applied undertile waterproofing membranes
- Existing ceramic tiles (internal dry areas)

SUBSTRATE PREPARATION

The surface being adhered to must be clean, firm and free of dust, dirt, oil, grease, curing compounds, release agents and other barrier materials, as well as being strong enough to support the weight of the tiles being fixed. Ensure surfaces are dry before tiling, with no residue or permanent damp. Ensure that the substrate's required drying time is allowed to elapse prior to fixing the tiles. Prime porous substrates with ARDEX Multiprime.

Concrete (including early age concrete)

Early age concrete must be a minimum of 7 days old and no less than 20 MPa. Prior to tiling, remove any concrete sealers or curing compounds from the surface, e.g. resin, wax sealers. Steel trowel finished concrete should be roughened mechanically to remove laitance and provide a good key for tiling. The surface should be true and level and pitched to drains where required. Smooth surfaces and/or dense concrete greater than 35 MPa must be mechanically roughened prior to tiling.

Cement Render/Screeds

New renders and screeds should be finished with a wood float to the required surface regularity. Screeds should be pitched to drains where required. Allow at least 16 hours to cure prior to tiling.

Plasterboard/Medium Density Fibre-Cement Sheet (Walls Only)

Tiles can be fixed directly provided these boards are firmly and rigidly fixed in accordance with manufacturer's instructions to adequately support the tile bed. Priming is recommended for fibre - cement sheet but is not usually necessary for plaster board except when jointing compound is used.

Compressed Fibre-Cement Sheet (Floors) Internal Applications

These sheets must be fixed strictly in accordance with manufacturer's instructions and be deemed suitable for the application by the manufacturer. Tiling over compressed fibre - cement sheet for external flooring applications should be carried out as per sheet

manufacturer's recommendations and local standard. ARDEX X 18 is not suitable for use over timber floors.

ARDEX Liquid Applied Undertile Waterproofing Membranes

ARDEX undertile waterproofing must be applied according to instructions and thoroughly dry prior to tiling.

Existing Ceramic Tiles (Internal Dry Areas Only)

These include sound, clean, glazed and unglazed tiles. Existing tiles must be firm and stable. Roughen the surface by mechanical means, clean off contamination and dust before tiling. Ensure that at least 80% of the glaze is removed. Tiling over existing tiles is not recommended in immersed applications.

MIXING

ARDEX X 18 powder is added to clean water in a large clean container whilst stirring vigorously and mixed thoroughly to give a lump free easily worked mortar of a thick creamy consistency. Allow to stand for 3 minutes. Re-stir the mixture thoroughly and the adhesive is ready for use.

A 25kg bag of ARDEX X 18 requires 6.25 - 7.5 Litres of water. The consistency of the adhesive can be slightly adjusted to suit site conditions and size, weight and type of tiles and location the tiles are to be fixed.

Do not apply at temperatures below 5°C. The pot life of the mixed mortar is approximately 3 hours at 23°C and 50% relative humidity and 50% RH.

For improved resilience to movement, and also in swimming pools, ARDEX X 18 can be mixed with ARDEX E90 in the following ratio 2.5 litres of E90 to 5.6 litres of cool water.

FIXING TECHNIQUE

Before fixing, ensure the substrate has been prepared and the tiles are free from dust. Substrate surface, type and size of the tiles will determine the selection of the trowel. As a general guide use a 6 x 6 x 6mm notch trowel for walls and 10 x 10 x 10mm notch trowel for floor tiling.

ARDEX X 18 can be applied at a bed thickness greater than 3mm or less than 10mm.

The tiles must be pressed firmly into the freshly combed mortar bed to ensure good contact with the mortar. Slide the tile at right angles to the notch pattern to ensure 100% coverage on the back of the tile. Tiles with ribbed or keyed back profiles should also be buttered to ensure complete coverage. Lift a tile from time to time to check that there are no voids beneath the tile. Do not spot fix. Any surplus adhesive must be removed from the surface of the tile and joints, before the adhesive sets.

ARDEX X 18 has an open time of 30 minutes and an adjustment time of 30 minutes. Please be aware of site conditions when considering these times and only spread enough adhesive so that the tiles can be fixed while the mortar is still wet. All tools should be cleaned with water immediately after use.

ARDEX X 18

Fibre Reinforced Flexible Non Slump Wall and Floor Tile Adhesive

GROUTING

Grouting can proceed once the tile bed has hardened sufficiently so that tiles will not be dislodged. Grouting and traffic may be allowed after approximately 24 hours at 23°C and 50% relative humidity. Allow longer for dense tiles/substrates, humid climates and low temperatures. The tile joints should be grouted with the appropriate ARDEX grout

COVERAGE

25kg of ARDEX X18 is sufficient for approx. 13.75 m² on walls, using a 6 x 6 x 6mm notched trowel and approx. 8.75 m² on floors using a 10 x 10 x 10mm notched trowel.

The coverage will vary depending on substrate condition, tile type and application technique.

PACKAGING

ARDEX X 18 is packed in polyline paper bag, net weight 25kg.

SHELF LIFE

ARDEX X 18 has a shelf life of not less than 12 months when stored in the original unopened packaging, in a dry place at 23°C and 50% relative humidity.

Pay attention to the following:

Do not use over metal or similar substrates. ARDEX X 18 is not suitable for use directly over timber floors. ARDEX X 18 should not be used on floors with a deflection greater than the joist span divided by 500 for tiles less than 600mm and divided by 700 for greater sized tiles.

ARDEX X 18 should not be used over substrates subject to shrinkage and other movement e.g. timber, ARDEX provides other systems. For setting of moisture sensitive natural stones, please refer to products in the ARDEX Natural Stone System.

Dimensional instability in natural stone ranges is often difficult to detect visually and may require thermal and moisture stability testing to ensure that adhesive recommendations can be warranted. Contact your tile supplier for further information or ARDEX technical services for information and testing,

TECHNICAL DATA

Colour:	Off white powder
Mixing ratio:	approx. 6.25 - 7.5L water per 25 kg
Application properties at 23°C and 50% RH	
Open time:	approx. 30 minutes
Sagging:	None
Adjustability time:	approx. 30 minutes
Grouting time:	approx. 24 hours
Pot Life:	approx. 3 hours
Mechanical properties (ISO 13007 / EN 12004) Tensile Adhesion Strength after	
28 days dry:	1 N / mm ²
Water immersion:	1 N / mm ²
Heat Ageing:	1 N / mm ²
Classification:	C2 TE S1

SAFETY PRECAUTIONS

This product is considered non hazardous in normal usage. The presence of cement in the product gives an alkaline mortar which may cause some irritation if prolonged contact with skin takes place. Avoid contact with skin and eyes; in case of contact with the eyes, rinse immediately with plenty of water and seek medical advice; wear suitable gloves and eye protection and keep the product out of the reach of children. Avoid generation of airborne dust during mixing. If swallowed do not induce vomiting, give a glass of water and contact a doctor.

For further material safety data, consult the latest Material Safety Data Sheet which is available upon request and online at www.ardex.com.sg

DISCLAIMER:

The technical datasheets are based on the latest information and given in good faith and represent the best of our knowledge and experience at the time of printing.

They are primarily offered for user's consideration and evaluation. It is the responsibility of the user to conduct their own tests to validate the suitability of the products. It is also the responsibility of the user to ensure that the products are used and handled correctly and in accordance with any applicable standards, the product instructions and recommendations and only for the uses they are intended. As we have no control over site conditions and the execution of the work, we accept no liability for any loss or damage which may rise as a result thereof. We also reserve the right to update the information at any time without prior notice to you to reflect our ongoing research and development program.

Offices:

Malaysia:

ARDEX MANUFACTURING SDN BHD (669180-X)

No. 35-1, Jalan Puteri 2/3, Bandar Puteri, 47100, Puchong, Selangor Darul Ehsan
Tel: +60 38060 1139 Fax: +60 38060 0719
Email: sales@ardex.com.sg

Thailand:

ARDEX (THAILAND) CO., LTD

969 2nd Floor Moo, 13, Soi 45, Bangna-Trad Road
Bangkaew, Bangplee, Samutprakarn 10540
Thailand
Tel: +66 2316 3069 Fax: +66 2316 3075
Email: sales@ardex.co.th

Vietnam:

Mobile: +84 901 351 308
Email: sales@ardex.com.sg

April 2020